

**Performance Summary**

- Enhanced soil + stain resistance
- Enhanced abrasion resistance
- Fluid barrier
- Contains an antimicrobial
- Bleach-solution cleanable
- Enhanced fade resistance

**Cleaning and Maintenance**

Cleaning code: **(W-S)** For water based stains use water based cleaning agents only, do not use solvents. For oil based stains use solvent cleaners only.

Bleach solutions of up to 10% may be used for cleaning difficult stains.

For additional cleaning information visit [cfstinson.com](http://cfstinson.com)

For complete specifications visit [cfstinson.com](http://cfstinson.com)

Dye lots may vary slightly from samples shown.

\*This term and any corresponding data refer to the typical performance in the tests indicated and should not be construed to imply the behavior of this or any other material under actual fire conditions.

\* Multiple factors affect fabric durability and appearance retention, including end-user application and proper maintenance. Wyzenbeek results above 100,000 double rubs have not been shown to be an indicator of increased lifespan.

**Specifications**

Content	Vinyl formulated without phthalates
Finish	Advanced Soil & Stain Protection
Backing	Polyester
Weight	29 oz. +/- 1.0 oz. per linear yard
Width	54"

**Performance Characteristics**

Abrasion Resistance * ASTM D4157	Exceeds 500,000 double rubs - Heavy Duty
Break Strength CFFA-17	Warp: 115 lbs. min., Fill: 102 lbs. min.
Tear Strength CFFA-16	Warp: 6.2 lbs. min., Fill: 7.9 lbs. min.
Seam Strength CFFA-14	Warp: 53.3 lbs. min., Fill: 49.6 lbs. min.
Colorfastness to Light AATCC 16	1000 Hrs, Class 4 min.
Crocking AATCC 8	Dry: Class 5, Wet: Class 5
Fluid Barrier	Inherent Fluid Barrier

**Flammability\***

California TB 117 - 2013, Section 1	Passes
IMO 2010 FTP Code Part 8	Passes
ASTM E 84 (Adhered & Unadhered)	Class A or 1
Boston Fire Code BFD IX-1	Passes
NFPA 260	Class 1
UFAC	Class 1
May contribute to compliance with California Technical Bulletin 133 when used in conjunction with other suitable components.	



# Stinson®

C.F. Stinson, LLC  
2849 Product Drive  
Rochester Hills, MI 48309

W [cfstinson.com](http://cfstinson.com)  
P 800 841 6279  
F 248 299 3884